

HIPLEX® HHM 5202

DESCRIPTION:

HIPLEX® HHM 5202, copolymer of ethylene and hexene, with relatively high molecular weight and medium molecular weight distribution, is blow moulding grade for production of small and medium size containers.

HIPLEX® HHM 5202 has good rigidity, hardness, impact strength, outstanding environmental stress cracking resistance and excellent processability.

PROCESSING RECOMMENDATIONS:

Processing temperature: 170-205 °C

PROPERTIES:

PROPERTY	TEST METHOD	UNIT	NOMINAL VALUE
MELT FLOW RATE	SRPS EN ISO 1133-1 190°C / 2.16 kg	g/10 min	0.20
DENSITY	SRPS EN ISO 1183-2	kg/m ³	951
TENSILE STRENGTH AT BREAK	SRPS EN ISO 527-2	MPa	30
TENSILE STRENGTH AT YIELD	SRPS EN ISO 527-2	MPa	24
ELONGATION AT BREAK	SRPS EN ISO 527-2	%	800
IZOD IMPACT STRENGTH	SRPS EN ISO 180	kJ/m ²	100
SHORE D HARDNESS	SRPS EN ISO 868	Shore D	64
ESC RESISTANCE, F ₅₀	SRPS EN ISO 22088-3 condition B	h	min. 100

SRPS – national standard

The values in this review are characteristic and are provided for guidance purposes only.

APPLICATION:

HIPLEX® HHM 5202 is suitable for production of small and medium size containers for packaging of bleach, chemicals and detergents.

HIPLEX® HHM 5202 has *Health Certificate* issued by Institute for Health Protection of Serbia. Also, **HIPLEX® HHM 5202** has *Statement of Conformity*, which declares product's conformity with the European norms for materials intended to come into contact with foodstuffs. *Statement of Conformity* is issued by National Laboratory of Health, Environment and Foods, Maribor, Slovenia.

X
E
L
P
H



PETROHEMIJA

STORAGE:

Polymer pellets are packed in LDPE bags, each bag weighs 25 kg. Bags are arranged on pallets and wrapped in stretch foil. One pallet has total polymer weight of 1250 kg.

Polyethylene is combustible material, therefore fire prevention measures in warehouses should be applied. Keep the polymer protected from harmful influences of heat, direct sunlight and high atmospheric humidity during storage.

If resin is stored under unfavourable conditions of large fluctuation in ambient temperature and atmospheric humidity, atmospheric moisture can condense inside the packaging. In such case, it is recommended to dry pellets before use.

The producer has no responsibility for any damage caused with the inappropriate storage.

REACH:

HIP-Petrohemija with applying the existing ISO 9001, ISO 14001, ISO 45001 and ISO 50001, follows completely the highest standards by which there are regulated environmental protection and human health and safety protection and herewith it expresses its intention to meet all the requirements which are prescribed by REACH regulation.

Registration of all the substances of potential export interest has been made with European Agency for Chemicals in Helsinki, in accordance with the prescribed deadlines, therefore in this way it enables further undisturbed placement and sale of HIP-Petrohemija's products without any limits at EU Market.

As the only representative for HIP-Petrohemija in EU, pursuant to Article 8 of REACH regulation, there has been designated **ReachLaw Ltd., Helsinki, Finland.**

RECYCLING:

Polyethylene is a material suitable for recycling.

The waste, that could appear during processing, should be kept clean before new usage through direct recycling.

CONTACT:

Sale:

T: +381 13 341 874

F: +381 13 347 173

E: polyolefins.sales@hip-petrohemija.rs

Technical information:

T: +381 13 307 103

F: +381 13 351 407

E: customer.support@hip-petrohemija.rs

X
E
L
P
I
H