

HIGH DENSITY POLYETHYLENE - HIPLEX®

HIPLEX® - commercial types

Property	Melt Flow Rate	Density	Tensile Strength at Yield	Tensile Strength at Break	Elongation	Izod Impact Strength	Hardness	ESC Resistance	Dart Drop (F50 method A)	Tear Strength (Elmendorf)	Application - commercial use of materials
Method	EN ISO 1133-1 190°C / 2.16 kg	EN ISO 1183-2	EN ISO 527-2 EN ISO 527-3	EN ISO 527-2 EN ISO 527-3	EN ISO 527-2 EN ISO 527-3	EN ISO 180	EN ISO 868	EN ISO 22088-3 method B ASTM D 1693	ASTM D 1709 EN ISO 7765-1	ASTM D 1922	
Unit	g/10 min	kg/m ³	MPa	MPa	%	kJ/m ²	Shore D	h	g	g/mil	

EXTRUSION BLOW MOULDING

HHM 5502	0.35	955	28	27	800	13	65	40	-	-	Small and medium size containers
HHM 5202	0.20	951	30	24	800	100	64	min 100	-	-	Small and medium size containers for surface active agents

FILM

TR 144	0.18	947	32 MD/TD 40/32**	21 MD/TD 24/19**	900 MD/TD 550/690**	14 no fracture	69	>1000	80*	MD/TD 25/550**	Tubular film
TR 130	0.18	940	32 MD/TD 43/33**	18 MD/TD 24/19**	800 MD/TD 550/700**	18 no fracture	58	>1000	88*	MD/TD 45/700**	Tubular film

PIPE EXTRUSION

TR 455 natur	0.50****	945	30	22	800	15	64	>1000	-	-	Gas pipes and potable water pipes
--------------	----------	-----	----	----	-----	----	----	-------	---	---	-----------------------------------

HIPLEX® - types on request under commercial sustainable conditions

EXTRUSION BLOW MOULDING

HXM 50100	10***	950	30	26	700	14 no fracture	64	>500	-	-	Medium and large size containers
-----------	-------	-----	----	----	-----	-------------------	----	------	---	---	----------------------------------

The values given in this review are typical and are provided for guidance purposes only. All HIPLEX® types are in pellet form if it is not specified otherwise.

NOTES: * results obtained at 25 µm film sample; blowup ratio 1:4
 ** results obtained at film sample in MD/TD direction MD – machine direction; TD – transversal direction
 *** melt flow rate 190°C / 21.6 kg
 **** melt flow rate 190°C / 5 kg

All HIPLEX® types have Health Certificate issued by Institute for Health Protection of Serbia. Types HHM 5502, HHM 5202, TR 144 and TR 130 also have Statement of Conformity, which declares product's conformity with the European norms for materials intended to come into contact with foodstuffs. Statement of Conformity is issued by National Laboratory of Health, Environment and Food, Maribor, Slovenia.

HIGH DENSITY POLYETHYLENE - HIPLEX®

It is produced in the HIP-Petrohemija under the licence from Phillips Petroleum Co (USA) and engineering made by Crawford & Russell (USA).

STORAGE

Polymer pellets are packed in classical or valve bags, each bag weighs 25 kg. Bags are arranged on pallets and wrapped in stretch foil. One pallet has total polymer weight of 1250 kg.

Polyethylene is combustible material, therefore fire prevention measures in warehouses should be applied. Keep the polymer protected from harmful influence of heat, direct sunlight and high atmospheric humidity during storage.

If resin is stored under unfavourable conditions of large fluctuation in ambient temperature and atmospheric humidity, atmospheric moisture can condense inside the packaging. In such case, it is recommended to dry pellets before use.

The producer has no responsibility for any damage caused with the inappropriate storage.

Sales:
 T: +381 13 341 874
 F: +381 13 347 173
 E: polyethylenes.sales@hip-petrohemija.rs

Technical information:
 T: +381 13 307 103
 F: +381 13 341 766
 E: customer.support@hip-petrohemija.rs

Address:
 HIP-Petrohemija a.d. Pancevo
 82Spoljnostarcevacka; 26000 Pancevo, Serbia
 Website:www.hip-petrohemija.com

REACH

HIP-Petrohemija with applying the existing standards ISO 9001:2008, ISO 14001:2004, OHSAS 18001:2007 and ISO 50001:2011 follows completely the highest standards by which human health and safety protection and environmental protection are regulated and herewith it expresses its intention to meet all the requirements which are prescribed by REACH regulation.

Registration of all the substances of potential export interest has been made with European Agency for Chemicals in Helsinki, in accordance with the prescribed deadlines, therefore in this way it enables undisturbed placement and sale of HIP-Petrohemija's products without any limits at EU Market. As the Only Representative for HIP-Petrohemija in EU, according to Article 8 of REACH regulation, ReachLaw Ltd, Helsinki, Finland has been designated.

RECYCLING

Polyethylene is a material suitable for recycling. The waste, that could appear during processing, should be kept clean before new usage through direct recycling.

